

Test Certificate

Page 1 of 1

Date Received 7 March 2005
Date Issued 17 March 2005
Client Aquarius Marine Coatings Limited
Shears Building
Stone Lane Industrial Estate
Wimborne
Dorset
BH21 1HD
FAO Mr J Kenny
PRA Reference 05/052/NP
Sample Submitted Coppercoat
Work Requested Total tin determination
Comments

The dried paint was analysed for total tin content using inductively coupled plasma (ICP) by an associated laboratory. That laboratory is accredited to ISO 17025 by the United Kingdom Accreditation Service (UKAS) to carry out this determination.

The total tin content in the dried paint is 325 mg/kg, which is in compliance with the allowed maximum content of 2500 mg tin/kg dry paint as stated in IMO Resolution MEPC.102(48).

Signed.....
Keith G Mower

Approved.....
Norman Falla
Head of Technology Support

Samples will be disposed of after 3 months